



PALSUN®

Flat Solid Polycarbonate Sheet



CONSTRUCTION



FABRICATION



SIGN & DISPLAY



ARCHITECTURE



Overview

PALSUN combines superior impact resistance and clarity, making it the material of choice for many demanding applications. It is virtually unbreakable, yet it is transparent as glass at less than half its weight.

PALSUN can be cold bent and easily fabricated and formed, making it ideal for barrel vault roofing, skylights, architectural roofing and glazing.

Clear, translucent and opaque PALSUN sheets are also ideal as machine guards, sound barriers, anti-vandal and safety glazing. PALSUN Diffuser and LB sheets are extensively used in durable light boxes.

Main Benefits

- High impact resistance - Virtually unbreakable
- High clarity and light transmission
- Weather and UV resistant
- Wide service temperature range
- Blocks harmful UV radiation
- Good acoustical insulation
- Lightweight
- Easy to handle and install
- Versatile, formable, and machinable



Typical Applications

Architecture

- Transparent acoustic barriers
- Sport venues
- Skylights
- Shopping centers
- Covered walkways

Construction

- Sun rooms and conservatories
- Pergolas and covered patios

Safety and Security Glazing

- Safety glazing
- Machine guards
- Bus stops and telephone booth
- Shields for police and security forces
- Glazing in public transportation
- Safety windshields for cars
- Eye protection visors for helmets

Sign & Graphics

- Signboards and illuminated signage
- Light Fixtures (white opal, diffused, or embossed sheets)

Fabrication

- Thermoformed, vacuum formed, bent, and fabricated items

www.palram.com



Standard Dimensions*

Thickness (mm)	Width x Length (mm)	Surface Finish				
		Smooth Both sides	Embossed Both sides	Matte One side	Hair Cell One side	Prismatic One side
1	1220 x 2440	✓		✓		
1.5	1250 x 2440	✓	✓	✓		
2		✓	✓	✓		
2.5 - 6	1220 x 2440	✓	✓	✓	✓	✓
8	2050 x 3050	✓	✓		✓	
9 - 12.7		✓			✓	
2 - 18	2450 x 3050	✓				


*Other dimensions are available upon request, subject to a minimum order.

Colors*

Transparent



Translucent



Opaque



*Custom colors and solar transmissions are available upon request, subject to a minimum order.

PALSUN® Product Range

Product	Description
PALTUF™	General purpose flat solid polycarbonate sheet for interior use
PALSUN®	Flat solid polycarbonate sheet, UV protected on one side
PALSUN® UV2	UV protection on both sides
PALSUN® Embossed*	Embossed surface (E102, prismatic, hair cell)
PALSUN® FR*	Fire retardant, better flammability ratings
PALSUN® Matte*	Matte finish on one side
PALSUN® LB*	Diffused sheet for light box applications
PALSUN® Solar Control*	Efficient heat-blocking with metallic appearance
PALSUN® Breeze*	Advanced heat-blocking with high transparency
PALGARD™	Abrasion resistance on one or both sides

* Available with UV protection on one or both sides.

Typical Physical Properties

Property	(Method*)	Conditions	Units	Value
Density	(D-792)		g/cm ³	1.2
Heat Deflection Temperature	(D-648)	Load: 1.82 MP	°C	130
Service Temperature - Short Term			°C	-50 to +120
Service Temperature - Long Term			°C	-50 to +100
Coefficient of Linear Thermal Expansion	(D-696)		mm/m °C	0.065
Thermal Conductivity	(C-177)		W/m K	0.21
Tensile Strength at Yield	(D-638)	10 mm/min.	MPa	65
Tensile Strength at Break	(D-638)	10 mm/min.	MPa	60
Elongation at Yield	(D-638)	10 mm/min.	%	6
Elongation at Break	(D-638)	10 mm/min.	%	>90
Tensile Modulus of Elasticity	(D-638)	1 mm/min.	MPa	2,300
Flexural Strength	(D-790)	1.3 mm/min.	MPa	100
Flexural Modulus	(D-790)	1.3 mm/min.	MPa	2,600
Impact Falling Weight	(ISO 6603/1 E50)	3mm sheet	J	158
Rockwell Hardness	(D-785)		R Scale	125R
Light Transmission	(D-1003)	3mm clear sheet	%	90
Haze	(D-1003)	3mm clear sheet	%	<0.5
Yellowness Index	(D-313)	3mm clear sheet	YI	<1

* ASTM except where noted.

Flammability

Product	Standard	Classification*
PALSUN®	EN13501	B, s1, d0
	BS 476/7	Class 1
	NSP 92501, 4	M2
	DIN 4102	B1
	UL Classified	V2 (File e221255)
	ASTM D-635	CC1
PALSUN® FR	Standard	Classification*
	UL 94	V0 (File e221255)

* Depends on thickness. For additional information please contact your Palram distributor.

Installation


Product masking (protective film) must be removed from both sides immediately after installation. Installation instructions are available from your PALRAM distributor upon request.



PALRAM H.Q.
Tel: +972.4.8459.900
Fax: +972.4.8444.980
palram@palram.com

PALRAM EUROPE LTD.
Tel: +44.1302.380777
Fax: +44.1302.380778
sales.europe@palram.com

PALRAM AMERICAS
Tel: 610.285.9918
Fax: 610.285.9928
palramamericas@palram.com



In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

